

Lemke Stone, Inc.

21575 W. Good Hope Road
Lannon, Wisconsin 53046

Phone: (262) 502-1579 Fax: (262) 502-1580
www.lemkestone.com

Sawed Cedar Creek Veneer

Ultimate Compression Strength

Dry Specimen 22,000-28,000psi

Absorption Rate less than ½%

Weight 169#/cubic foot