

Lemke Stone, Inc.

P.O. Box 428
215755 W. Good Hope Road
Lannon, Wisconsin 53046
(262) 502-1579

LANNON STONE

Ultimate Compressive Strength

Dry Specimen 22,000-28,000 psi

Absorption Rate Less than 1/2%

Weight 169#/cubic foot